

Omya International AG P.O. Box CH-4665 Oftringen

+41 62 789 29 29 +41 62 789 20 77

www.omya.com

Omyacarb® 95 T - KA

PRODUCTION SITE: KARABIGA, Turkey

(certified ISO 9001, ISO 14001 and ISO 45001)

SHORT DESCRIPTION OF

THE PRODUCT:

Natural, surface treated, very fine, easy to disperse calcium carbonate powder obtained from high purity white marble. The surface treatment results in excellent dispersion properties and renders the product completely hydrophobic.

CHEMICAL ANALYSIS:	CaCO ₃	98	%
	MgCO ₃	1.7	%
	Fe ₂ O ₃	0.05	%
	HCl insoluble content	0.2	%
SPECIFIC PRODUCT DATA:	Fineness: #		
	· Residue on a 45 µm sieve (ISO 787-7)	0.01	%
	· Top cut (d98%)	4.3	μm
	· Median particle size (d50%)	1.3	μm
	· Particles < 2 µm	71	%
	Optical properties:		
	Brightness Ry (C/2°, DIN 53163)	94.5	%
	CIE L*, a*, b* (ISO 11664-4)	97.9/0.05/0.8	
	Yellowness index (DIN 6167)	1.5	
*measured on untreated material	Moisture ex works (ISO 787-2)	0.4	%
GENERAL PRODUCT DATA:	Apparent density, tamped (ISO 787-11)	1.1	g/ml
	pH value (ISO 787-9)	9.5	J

Oil absorption (ISO 787-5)


VO absorption (ISO 787-5)

MAIN APPLICATIONS:

Plastics

- PVC foams
- Rigid PVC
 - Window profiles
 - Profiles/pipes
 - Mouldings
 - Calendered sheets
- Polyolefins
 - Colour masterbatch
 - Compound/masterbatch for mouldings/film

PARTICLE SIZE DISTRIBUTION (Sedigraph):



The information contained in this Technical Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process. The information provided herein is based on technical data that Omya believes to be reliable, however Omya makes no representation or warranty as to the completeness or accuracy thereof and Omya assumes no liability resulting from its use or for any claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgement as to the appropriateness of its use, and it is the user's responsibility to assess the material's suitability (including safety) for a particular purpose prior to such use.

g/100g

g/100g

20