ARGON

TDS

# ARAKRIL®SB 80

Arakril SB 80 is an APEO and formaldehyde free anionic-nonionic styrene acrylic copolymer emulsion.

## **Specification**

	UNIT	VALUE	TEST METHOD
Solid Content 1/2h 150°C	%	40±1	DIN EN ISO 3251
рН		6.0-8.0	DIN ISO 976
Viscosity Brookfield RVDV-II	mPas	50-500	DIN EN ISO 2555

#### **Additional Data**

These data are used solely to describe the product. They are not subject to constant monitoring or part of the specification.

	UNIT	VALUE	TEST METHOD
MFFT	°C	<0	ISO 2115
Density	g/cm³	1,04	ISO 8962
Ionic Charge	Anionic-Nonionic		
Film Appearance	Clear and Tacky		
Тд	°C	-7±2	DIN 53 765(DSC)

# **Recommended Application Areas**

**Textile Pigment Printing** 

#### **Application**

Arakril SB 80 is a styrene acrylic polymer emulsion particularly for textile pigment printing. It gives a soft handle at all types of pigment printing. The amount of thickener needed in the printing paste is at the minimum level. It can be used for all types of pigment printing machines (rotational, flat) at all conditions. The required amount of Arakril SB 80 is 10-15 % in the printing paste.

It is preferred particularly for 1:1 cotton- polyamide mixture fabrics. The wet and dry fastness properties of Arakril SB 80 are excellent.

The closure of the container should be closed tightly after necessary amount of material is taken to preserve the homogeneity of the material safely.

determine the suitability of the materials before adapting them on a commercial scale.



# Polymer Emulsions

TDS

### **Shelf-life and Storage**

The dispersion contains some initial preservatives to prevent attact by micro organisms. In order that the product is also sufficiently protected against microbial contamination during further storage in opened drums or storage tanks a suitable preservative should be added despite our preliminary preservation measures. Checks should be carried out to determine their compatibility and efficacy. The tanks and pipework should be kept adequately clean.

Arakril SB 80 should not be stored for longer than 12 months before processing as far as possible, storage should be at a uniform temperature in the region of 5-35°C. The product should, in principle, be kept away from frost and direct exposure to sunshine. Furthermore it must be ensured that already opened drums or containers are always tightly closed.

The technical data ascertained by our quality control laboratory at the time of product release may vary according to storage time and storage conditions and may deviate from the stated limits.

These technical data and suggestions are based on the information we believe to be reliable and are given in good faith but without guarantee, as conditions and methods of use are beyond our control. The prospective user should apply our products to their own working conditions and determine the suitability of the materials before adapting them on a commercial scale.

January 2013 (Version 2)