

ARAKRIL® STA 257

Arakril STA 257 is a plasticizer free, APEO and formaldehyde free anionic styrene acrylic copolymer emulsion.

Specification

	UNIT	VALUE	TEST METHOD
<i>Solid Content 1/2h 150°C</i>	%	57±1	DIN EN ISO 3251
<i>pH</i>		7.0-9.0	DIN ISO 976
<i>Viscosity Brookfield RVDV-II</i>	mPas	Max 1500	DIN EN ISO 2555

Additional Data

These data are used solely to describe the product. They are not subject to constant monitoring or part of the specification.

	UNIT	VALUE	TEST METHOD
<i>MFFT</i>	°C	<0	ISO 2115
<i>Density</i>	g/cm ³	1,04	ISO 8962
<i>Ionic Charge</i>		Anionic	
<i>Film Appearance</i>		Clear and Tacky	
<i>Tg</i>	°C	-10±2	DIN 53 765(DSC)

Recommended Application Areas

Tile adhesives & sealants
Two component adhesive mortars
Insulating coatings with cement
Roof coatings

Application

Arakril STA 257 is particularly designed for the formulation of exterior coating systems like moisture barrier coatings with high performance adhesion and scrub resistance properties.

Arakril STA 257 is also employed in two component cement based coating systems due to its high binding capacity and excellent flexibility.

It is also suitable to be utilized in the production of crack-sealing or crack-filling systems and flexible cement-containing coatings for flat roofs and walls.



Shelf-life and Storage

The dispersion contains some initial preservatives to prevent attack by micro organisms. In order that the product is also sufficiently protected against microbial contamination during further storage in opened drums or storage tanks a suitable preservative should be added despite our preliminary preservation measures. Checks should be carried out to determine their compatibility and efficacy. The tanks and pipework should be kept adequately clean.

Arakril STA 257 should not be stored for longer than 12 months before processing as far as possible, storage should be at a uniform temperature in the region of 5-35°C. The product should, in principle, be kept away from frost and direct exposure to sunshine. Furthermore it must be ensured that already opened drums or containers are always tightly closed.

The technical data ascertained by our quality control laboratory at the time of product release may vary according to storage time and storage conditions and may deviate from the stated limits.